

Chesapeake Bay

- Available in Double 4.5" and Double 4.5"Dutchlap profile.
- Outstanding beauty that will last a lifetime.
- Deep cedar wood grain finish that's perfect for remodeling and new homes.
- The color is actually part of the siding material itself, so nicks and scratches won't show.
- Rugged good looks.
- Timeless design and a solid value.
- Comes with a complete color coordinated range of trims and accessories to add that special finishing touch to your design.
- .042 thickness that retains strength, stability and good looks year after year.
- Virtually maintenance free - never needs painting.
- Superior value and low maintenance performance in all environments



Manufacturer

Materials to be supplied by Continental Manufacturing LLC, 800 S Wellington, Richmond, MO 64085.

Materials

All of the vinyl siding shall be extruded Poly Vinyl Chloride (PVC) and shall conform to the following requirements established by ASTM Specifications D 3679, developed in cooperation with the industry and published by the American Society for Testing and Materials.

Typical Compound Properties

Tensile Strength: ASTM D638 6,040 psi
Tensile Modulus: ASTM D638 365,000 psi
Flexural Strength: ASTM D790 11,500 psi
Flexural Modulus: ASTM D790 410,000 psi
Izod 73°F Method A 17.0 ft-lb/in

VSI Flammability

Burn Length (0.040 in Bar) ASTM D635 0* IN. Burn Time (0.040 in Bar) ASTM D635 0* Sec
Drop Dart Impact Resistance Procedure A, 73° F ASTM D4226 1.9 in-lb/mil
Drop Dart Impact Resistance Procedure B, 73° F ASTM D4226 4.0 in-lb/mil
Vulcanizate Properties Hardness Instantaneous, D ASTM D2240 83
Thermal Properties HDT Unannealed, 264 psi ASTM D648 162 °F
Coeff of Linear Thermal Expansion ASTM D696 3.6EO in/in/°F
Gloss: plus or minus 5 units, ASTM D3679
Surface Distortion: No Distortion at 105°F, ASTM D3679
Weatherability: No surface or structural defects when tested as per ASTM D3679

Siding Dimensions and Description

Chesapeake Bay D4.5 and D4.5 Dutchlap, horizontal siding panel, 9 in. wide exposure configured as two 4.5" in. panels, 12' & 16'8" lengths. Thickness 0.042 in. ±0.002 in.
Embossed Wood Grain: Color to match the samples provided.
Interlock: Siding panels are made with post form style lock with positive interlock.
Both ends of the panel are factory cut and notched for overlap.
Weep holes: Small holes under the bottom butt prevent vapor build up and allow accumulated moisture to escape.

Continental Manufacturing LLC | 800 S Wellington | Richmond, MO 64085

Phone: 816-776-3111 | Fax: 816-776-3555 | www.sidingmfg.com